



Albi Manufacturing
Division of StanChem, Inc.
401 Berlin St., East Berlin, CT 06023
860/828-0571 Fax: 860/828-3297
<http://www.albi.com>

ALBI CLAD 800
U.L. 1709 LISTINGS

COLUMNS: W10X49

FIRE TEST: UL 1709 HYDROCARBON

| APPLICATION CONTOUR | U.L. DESIGN NO. | HOURLY RATING | MATERIAL THICKNESS | REINFORCEMENT |
|--------------------------------|----------------------------|--------------------------|-------------------------------|----------------------|
| | XR-602 | 1 hr. | .20 in. dry | wire mesh |
| | XR-602 | 1-1/2 hrs. | .41 in. dry | wire mesh |
| | XR-602 | 2 hrs. | .76 in. dry | wire mesh |
| | XR-607 | 1 hr. | .25 in. dry | none |
| | XR-608 | 1-1/2 hrs. | .35 in. dry | fiberglass ribbon |
| | XR-608 | 2 hrs. | .51 in. dry | fiberglass ribbon |
| | XR-609 | 2-1/2 hrs. | .62 in. dry | fiberglass ribbon |
| | XR-609 | 3 hrs. | .75 in. dry | fiberglass ribbon |

COLUMNS: 8 INCH PIPE

FIRE TEST: UL 1709 HYDROCARBON

| APPLICATION CONTOUR | U.L. DESIGN NO. | HOURLY RATING | MATERIAL THICKNESS | REINFORCEMENT |
|--------------------------------|----------------------------|--------------------------|-------------------------------|----------------------|
| | XR-603 | 1 hr. | 0.31 in. dry | wire mesh |
| | XR-603 | 1-1/2 hrs. | 0.58 in. dry | wire mesh |
| | XR-603 | 2 hrs. | 0.98 in. dry | wire mesh |