



BXUV.Y649 - FIRE-RESISTANCE RATINGS - CAN/ULC-S101 CERTIFIED FOR CANADA

Design/System/Construction/Assembly Usage Disclaimer

- Authorities Having Jurisdiction should be consulted in all cases as to the particular requirements covering the installation and use of UL Certified products, equipment, system, devices, and materials.
- Authorities Having Jurisdiction should be consulted before construction.
- Fire resistance assemblies and products are developed by the design submitter and have been investigated by UL for compliance with applicable requirements. The published information cannot always address every construction nuance encountered in the field.
- When field issues arise, it is recommended the first contact for assistance be the technical service staff provided by the product manufacturer noted for the design. Users of fire resistance assemblies are advised to consult the general Guide Information for each product category and each group of assemblies. The Guide Information includes specifics concerning alternate materials and alternate methods of construction.
- Only products which bear UL's Mark are considered Certified.

BXUV - Fire Resistance Ratings - ANSI/UL 263 Certified for United States

BXUV7 - Fire Resistance Ratings - CAN/ULC-S101 Certified for Canada

See General Information for Fire-resistance Ratings - ANSI/UL 263 Certified for United States Design Criteria and Allowable Variances


See General Information for Fire Resistance Ratings - CAN/ULC-S101 Certified for Canada Design Criteria and Allowable Variances

Design No. Y649

July 26, 2019

Ratings — 1, 1-1/2, 2, 3 and 4 Hr. (See Item 2)

*** Indicates such products shall bear the UL or cUL Certification Mark for jurisdictions employing the UL or cUL Certification (such as Canada), respectively.**



1. **Steel Column** — Wide flange steel columns with the minimum sizes shown in the tables below. Columns shall be free of dirt, loose scale and oil. Columns shall be primed with a phenolic modified alkyl resin primer.

2. **Mastic and Intumescent Coatings*** — Coating spray, brush or trowel applied directly from containers to desired thickness. See tables below for appropriate final dry thickness and applicable rating.

Steel Size	W/D	1-1/2 Hr				
		1 Hr Min Thickness, In.	Min Thickness, In.	2 Hr Min Thickness, In.	3 Hr Min Thickness, In.	4 Hr Min Thickness, In.
W8 x 10	0.33	0.145	0.266	NR	NR	NR
W12 x 14	0.36	0.133	0.263	NR	NR	NR
W12 x 16	0.41	0.117	0.230	NR	NR	NR
W6 x 12	0.44	0.109	0.215	0.338	NR	NR
W8 x 15	0.48	0.100	0.197	0.310	NR	NR
W10 x 22	0.52	0.092	0.182	0.286	NR	NR
W4 x 13	0.55	0.087	0.172	0.271	NR	NR
W6 X 16	0.58	0.083	0.163	0.257	0.504	NR
W8 x 24	0.59	0.075	0.130	0.213	0.504	NR
W14 x 34	0.63	0.075	0.130	0.213	0.489	NR
W8 x 28	0.68	0.070	0.130	0.213	0.453	NR
W8 x 35	0.74	0.065	0.128	0.201	0.416	NR

W10 x 39	0.78	0.061	0.121	0.191	0.395	NR
W10 x 49	0.84	0.057	0.113	0.177	0.367	NR
W10 x 45	0.89	0.054	0.106	0.167	0.346	NR
W16 x 57	0.95	0.050	0.099	0.157	0.324	NR
W8 x 48	1.00	0.048	0.095	0.149	0.308	NR
W14 x 90	1.07	0.045	0.088	0.139	0.288	NR
W10 x 68	1.14	0.042	0.083	0.131	0.270	NR
W18 x 97	1.21	0.040	0.078	0.123	0.255	NR
W10 x 77	1.28	0.038	0.074	0.116	0.241	NR
W16 x 100	1.36	0.036	0.069	0.109	0.227	NR
W10 x 88	1.45	0.034	0.065	0.103	0.213	NR
W14 x 132	1.54	0.032	0.061	0.097	0.200	NR
W12 x 120	1.64	0.030	0.058	0.091	0.188	NR
W14 x 159	1.77	0.028	0.056	0.085	0.187	NR
W14 x 176	1.95	0.025	0.051	0.077	0.178	NR
W14 x 193	2.12	0.023	0.047	0.071	0.164	NR
W14 x 211	2.30	0.023	0.043	0.066	0.151	NR
W14 x 233	2.52	0.023	0.040	0.060	0.138	NR
W14 x 257	2.75	0.023	0.036	0.055	0.126	NR
W14 x 283	3.00	0.023	0.033	0.050	0.116	0.194

NR = No Rating

As an alternate to the above table, the required thickness of coating (in inches) to be applied to all surfaces of wide flange steel columns for 1 hour ratings, in the W/D range of 0.33 to 1.14, may be determined from the following equation:

$$T = 0.04785/(W/D)$$

Where T = Thickness of coating in the range of 0.042 to 0.145 in., W = Weight of steel column in pounds per linear foot, D = Heated perimeter of steel column section in inches.

As an alternate to the above table, the required thickness of coating (in inches) to be applied to all surfaces of wide flange steel columns for 1-1/2 hour ratings, in the W/D range of 0.33 to 1.64, may be determined from the following equation:

$$T = 0.0945/(W/D)$$

Where T = Thickness of coating in the range of 0.058 to 0.266 in., W = Weight of steel column in pounds per linear foot, D = Heated perimeter of steel column section in inches.

As an alternate to the above table, the required thickness of coating (in inches) to be applied to all surfaces of wide flange steel columns for 2 hour ratings, in the W/D range of 0.44 to 1.64, may be determined from the following equation:

$$T = 0.1489/(W/D)$$

Where T = Thickness of coating in the range of 0.091 to 0.338 in., W = Weight of steel column in pounds per linear foot, D = Heated perimeter of steel column section in inches.

As an alternate to the above table, the required thickness of coating (in inches) to be applied to all surfaces of wide flange steel columns for 3 hour ratings, in the W/D range of 0.58 to 1.64, may be determined from the following equation:

$$T = 0.3082/(W/D)$$

Where T = Thickness of coating in the range of 0.188 to 0.504 in., W = Weight of steel column in pounds per linear foot, D = Heated perimeter of steel column section in inches.

As an alternate to the above, the following table listing metric units may be used.

Steel Size	M/D	Hp/A	1-1/2 Hr				
			1 Hr Min Thickness, mm	1 Hr Min Thickness, mm	2 Hr Min Thickness, mm	3 Hr Min Thickness, mm	4 Hr Min Thickness, mm
W8 x 10	19.1	412	3.68	6.76	NR	NR	NR
W12 x 14	21.2	371	3.38	6.67	NR	NR	NR
W12 x 16	24.0	327	2.96	5.85	NR	NR	NR
W6 x 12	25.9	303	2.76	5.46	8.60	NR	NR
W8 x 15	28.1	280	2.53	5.00	7.88	NR	NR
W10 x 22	30.4	258	2.34	4.62	7.27	NR	NR
W4 x 13	32.4	242	2.21	4.36	6.88	NR	NR
W6 X 16	33.9	232	2.10	4.14	6.52	12.80	NR
W8 x 24	34.6	227	1.91	3.31	5.42	12.80	NR
W14 x 34	37.1	213	1.91	3.31	5.42	12.43	NR

W8 x 28	40.0	197	1.79	3.31	5.42	11.51	NR
W8 x 35	43.6	181	1.64	3.24	5.11	10.58	NR
W10 x 39	45.4	172	1.56	3.08	4.85	10.04	NR
W10 x 49	49.1	159	1.45	2.86	4.50	9.32	NR
W10 x 45	51.9	151	1.37	2.70	4.25	8.80	NR
W16 x 57	55.9	141	1.28	2.53	3.98	8.24	NR
W8 x 48	58.6	134	1.22	2.40	3.78	7.83	NR
W14 x 90	62.6	125	1.14	2.24	3.53	7.32	NR
W10 x 68	66.9	118	1.07	2.11	3.32	6.87	NR
W18 x 97	71.0	111	1.02	1.98	3.13	6.47	NR
W10 x 77	75.2	105	0.97	1.88	2.95	6.12	NR
W16 x 100	79.4	99	0.91	1.76	2.78	5.76	NR
W10 x 88	84.9	92	0.85	1.66	2.61	5.40	NR
W14 x 132	90.0	87	0.80	1.56	2.46	5.08	NR
W12 x 120	96.2	82	0.75	1.46	2.31	4.77	NR
W14 x 159	103.9	76	0.70	1.43	2.16	4.74	NR
W14 x 176	114.4	69	0.63	1.30	1.96	4.52	NR
W14 x 193	124.4	63	0.59	1.19	1.81	4.16	NR
W14 x 211	135.0	58	0.59	1.10	1.66	3.83	NR

W14 x 233	147.9	53	0.59	1.00	1.52	3.50	NR
W14 x 257	161.4	49	0.59	0.92	1.39	3.21	NR
W14 x 283	176.0	45	0.59	0.84	1.28	2.94	4.92

NR = No Rating

As an alternate to the above table, the required thickness of coating (in mm) to be applied to all surfaces of wide flange steel columns for 1 hour ratings, in the M/D range of 19.1 to 66.9, may be determined from the following equation:

$$T = 71.6/(M/D)$$

Where T = Thickness of coating in the range of 1.07 to 3.68 mm, M = Weight of steel column in kilograms per linear meter, D = Heated perimeter of steel column section in meters.

As an alternate to the above table, the required thickness of coating (in mm) to be applied to all surfaces of wide flange steel columns for 1-1/2 hour ratings, in the M/D range of 19.1 to 96.2, may be determined from the following equation:

$$T = 141.3/(M/D)$$

Where T = Thickness of coating in the range of 1.46 to 6.76 mm, M = Weight of steel column in kilograms per linear meter, D = Heated perimeter of steel column section in meters.

As an alternate to the above table, the required thickness of coating (in mm) to be applied to all surfaces of wide flange steel columns for 2 hour ratings, in the M/D range of 25.9 to 96.2, may be determined from the following equation:

$$T = 222.7/(M/D)$$

Where T = Thickness of coating in the range of 2.31 to 8.60 mm, M = Weight of steel column in kilograms per linear meter, D = Heated perimeter of steel column section in meters.

As an alternate to the above table, the required thickness of coating (in mm) to be applied to all surfaces of wide flange steel columns for 3 hour ratings, in the M/D range of 33.9 to 96.2, may be determined from the following equation:

$$T = 461.0/(M/D)$$

Where T = Thickness of coating in the range of 4.77 to 12.80 mm, M = Weight of steel column in kilograms per linear meter, D = Heated perimeter of steel column section in meters.

ALBI MFG, DIV OF STANCHEM INC — Type Albi Clad TF+. Investigated for Interior General Purpose.

*** Indicates such products shall bear the UL or cUL Certification Mark for jurisdictions employing the UL or cUL Certification (such as Canada), respectively.**

Last Updated on 2019-07-26

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under UL's Follow-Up Service. Only those products bearing the UL Mark should be considered to be Certified and covered under UL's Follow-Up Service. Always look for the Mark on the product.

UL permits the reproduction of the material contained in the Online Certification Directory subject to the following conditions: 1. The Guide Information, Assemblies, Constructions, Designs, Systems, and/or Certifications (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from the Online Certifications Directory with permission from UL" must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: "© 2019 UL LLC"

