

Heavy Duty Clear Polyurethane, Product #544

Description: A high solids, clear or satin finish that provides an exceptional hard abrasion and mar resistant protective coating for wood and metal. Excellent use in homes and industry as well as boats and other marine uses. Polyurethane is a super-tough clear protective coating that flows out to a super smooth gloss or satin finish. Polyurethane's quick-dry and extreme durability makes it the most widely used finish in the flooring industry.

Color(s): Clear

Finish: High Gloss, Satin

Vehicle type: Polyurethane

Solvent type: Mineral Spirits

VOC: 3.6 Lbs/Gallon (432 Grams/Liter)

Flash point: 105° F. Seta Flash

Solids by volume: 45%

Weight per gallon: 7.5 Lbs

Coverage: Theoretical coverage at 1 mil dry is 772 square feet per gallon, and 361 square feet at 2 mils dry.

Viscosity: 40 Seconds (#4 ford cup)

Surface preparation: Remove all grease, dirt, oil, wax and other foreign matter from surface. New Wood: Apply first coat of polyurethane on clean, bare wood. Do not use wood paste, filler, shellac or wood sealers that contain stearates. Old work: If old varnish is in good condition screen surface before applying new coat. If flaked or peeling exists sand floor completely.

Shelf life: 12 Months

Mixing: Stir thoroughly and apply as it comes from the container

Recommended dry film: 2 Mil

Recommended dry time: Dries in 4 Hours. Can be re-coated in 12 hours.

Recommended primers: N/A

Safety information: COMBUSTIBLE! HARMFUL OR FATAL IF SWALLOWED, CONTAINS MINERAL SPIRITS. Keep away from heat, sparks and flame. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase air or wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave area. Do not take internally. Close container after each use. Avoid contact with skin or eyes.

Dux Paint LLC.

18 Mill Street, Lodi NJ 07644

Office - (973)-473-2376, Fax - (973)-473-1648